Efectis Nederland BV
P.O. Box 554 | 2665 ZN Bleiswijk
Brandpuntlaan Zuid 16 | 2665 NZ Bleiswijk
The Netherlands
+31 88 3473 723
nederland@efectis.com

CLASSIFICATION OF REACTION TO FIRE PERFORMANCE IN ACCORDANCE WITH EN 13501-1:2018

Classification no.	2025-Efectis-R001018[Rev.1]
Sponsor	TRESPA INTERNATIONAL B.V. Wetering 20 6002 SM WEERT THE NETHERLANDS
Product name	**Trespa® Meteon® FR**
Prepared by	Efectis Nederland BV
Author(s)	Robin Timmermans Job Onderwater Suzanne van Herp
Project number	ENL-25-000656
Original date of issue	December 2025
Date of first revision	January 2026
Number of pages	13

All rights reserved.
No part of this publication may be reproduced and/or published without the previous written consent of Efectis Nederland BV.
Submitting the report for inspection to parties who have a direct interest is permitted.

In case this report was drafted on instructions, the rights and obligations of contracting parties are subject to either the Standard Conditions of Efectis Nederland BV or the relevant agreement concluded between the contracting parties.

© 2025 Efectis Nederland BV

www.trespa.info - IP: 104.23.229.68 - Downloaded on: 2026-10-07 10:55:41
Disclaimer applies. Information indicative and for general informational purposes only. Refer to website terms of use.

1. REVISION INFORMATION

This is a revised version of this report. This version supersedes all previous versions of this reports that are hereby withdrawn. Details on the changes can be found in the tables below.

Table 1.1: Revision information

Issue	Date of issue	Report no.
First issue	December of 2025	2025-Efectis-R001018
First revision	January of 2026	2025-Efectis-R001018[Rev. 1]

1.1.1 First revision detailed information

Table 1.2: First revision information

Chapter of revision	Chapter 3: Details of classified product Chapter 5: Classification and field of application
Reason of revision	EN 438-6 was not specified as EN 438-6:2016. EN 438-7 was not specified as EN 438-7:2005.
Consequences of revision	None

Table 1.3: First revision information

Chapter of revision	Chapter 3: Details of classified product
Reason of revision	The finishes Rock and Matt were not mentioned in the list. Both finishes are added in the product description.
Consequences of revision	Extension of the field of application

Table 1.4: First revision information

Chapter of revision	Chapter 4: Standards, reports, results and criteria in support of this classification
Reason of revision	The finish ‘Printed decors’ were mentioned as ‘Printed’ in multiple tables. The term ‘decors’ is added for clarity.
Consequences of revision	The type of finish used in the product is clarified.

Table 1.5: First revision information

Chapter of revision	Chapter 4: Standards, reports, results and criteria in support of this classification
Reason of revision	In paragraph 4.3.6 and 4.3.7, it was not mentioned if the test specimens were double- or single-sided. In both cases, it was added that the specimens were tested as double-sided.
Consequences of revision	The tested specimens were clarified to be double-sided.

www.trespa.info - IP: 104.23.229.68 - Downloaded on: 2026-10-07 10:55:41
Disclaimer applies. Information indicative and for general informational purposes only. Refer to website terms of use.

Table 1.6: First revision information

Chapter of revision	Chapter 5: Classification and field of application
Reason of revision	In paragraph 5.3.1, the surface density was mentioned to be ≤ 11.2 kg/m^2. This is corrected to ≥ 11.2 kg/m^2.
Consequences of revision	The application of the product is valid for products with a surface density equal or higher than 11.2 kg/m^2.

Table 1.7: First revision information

Chapter of revision	Chapter 5: Classification and field of application
Reason of revision	The term printed, in the direct field of application, should be mentioned as printed decors. This is corrected.
Consequences of revision	The printed decor finish is valid in all colours.

2. INTRODUCTION

2.1 PRODUCT NAME

This classification report defines the classification assigned to **Trespa® Meteon® FR** in accordance with the procedures given in EN 13501-1:2018.

2.2 ASSESSMENT INFORMATION

Efectis reviewed the test results provided by Warrington Fire via Trespa International of the EN ISO 11925:2020 and EN 13823:2020 tests and concluded that the results from the tests are still valid. This report can, therefore, be used for classification according to EN 13501-1:2018.

3. DETAILS OF CLASSIFIED PRODUCT

3.1 GENERAL

The product, **Trespa® Meteon® FR**, is defined as a wall covering.

3.2 MANUFACTURER

TRESPA INTERNATIONAL B.V.
Wetering 20
6002 SM WEERT
THE NETHERLANDS

3.3 PRODUCT DESCRIPTION

Product description:
The product, Trespa® Meteon® FR, is defined as compact laminate panels for external wall and ceiling finishes. Type EDF according to EN 438-6:2016.

The material consists of kraft paper impregnated with phenolic resin and a coating on the outside with acrylic resin. The product has a thickness of 8 mm and density of 1350 kg/m^3. The organic and fire-retardant content details are available at the sponsor.

www.trespa.info - IP: 104.23.229.68 - Downloaded on: 2026-10-07 10:55:41
Disclaimer applies. Information indicative and for general informational purposes only. Refer to website terms of use.

The product is available in different finish:

- Satin
- Rock
- Diffuse
- Oblique
- Specular
- Matt-Rock
- Matt

The product is available in multiple colour ranges named as below:

- UNI (A, L)
- Printed decors (NA, NM, NW, C, CM)
- Metallics (M, LM)

4. STANDARDS, REPORTS, RESULTS AND CRITERIA IN SUPPORT OF THIS CLASSIFICATION

4.1 APPLICABLE (PRODUCT) STANDARDS

EN ISO 11925-2:2020	Reaction to fire tests - Ignitability of products subjected to direct impingement of flame - Part 2: Single-flame source test
EN 13823:2020+A1:2022	Reaction to fire tests for building products - Building products, excluding floorings exposed to the thermal attack by a single burning item
EN 13238:2010	Reaction to fire tests for building products - Conditioning procedures and general rules for selection of substrates
EN 13501-1:2018	Fire classification of construction products and building elements Part 1: Classification using data from reaction to fire tests
NEN EN 438-7:2005	High pressure decorative laminates (HPL) - Sheets based on thermosetting resins (usually called Laminates – Part 7: Compact laminates and HPL composite panels for internal and external wall and ceiling finishes.

4.2 REPORTS

Name of Laboratories	Name of sponsor	Report ref. no.	Test method
WFRGENT N.V. BELGIUM	TRESPA INTERNATIONAL B.V THE NETHERLANDS	22082B 22082C 22082A 22082D 22082E 22082F 22082G	EN ISO 11925-2:2020 EN 13823:2020+A1:2022
Efectis Nederland BV THE NETHERLANDS	TRESPA INTERNATIONAL B.V THE NETHERLANDS	2025-Efectis-R001691	EN 13823:2020+A1:2022

www.trespa.info - IP: 104.23.229.68 - Downloaded on: 2026-10-07 10:55:41
Disclaimer applies. Information indicative and for general informational purposes only. Refer to website terms of use.

4.3 TEST RESULTS

4.3.1 Test report No. 22082B – Colour difference review

Test method and test number	Parameter	No. tests	Results	
			Continuous parameter – maximum	Compliance with parameters
EN ISO 11925-2				
Kraft + F30 – M53.0.1 – Satin – 8 mm (Metallics)				
Surface flame Impingement	Fs ≤150 mm	6	30	-
	Ignition of filter paper		-	Compliant
Edge flame Impingement	Fs ≤150 mm	6	25	-
	Ignition of filter paper		-	Compliant
Kraft + F30 – M51.0.1 – Satin – 8 mm (Metallics)				
Surface flame impingement	Fs ≤150 mm	6	30	-
	Ignition of filter paper		-	Compliant
Edge flame Impingement	Fs ≤150 mm	6	30	-
	Ignition of filter paper		-	Compliant
Kraft + F30 – LM21.8.1 – Oblique – 8 mm (Metallics)				
Surface flame impingement	Fs ≤150 mm	6	40	-
	Ignition of filter paper		-	Compliant
Edge flame Impingement	Fs ≤150 mm	6	30	-
	Ignition of filter paper		-	Compliant
Kraft + F30 – A12.1.8 – Satin – 8 mm (UNI)				
Surface flame impingement	Fs ≤150 mm	6	30	-
	Ignition of filter paper		-	Compliant
Edge flame Impingement	Fs ≤150 mm	6	30	-
	Ignition of filter paper		-	Compliant
Kraft + F30 – A05.0.0 – Satin – 8 mm (UNI)				
Surface flame impingement	Fs ≤150 mm	6	25	-
	Ignition of filter paper		-	Compliant
Edge flame Impingement	Fs ≤150 mm	6	25	-
	Ignition of filter paper		-	Compliant
Kraft + F30 – L90.0.0 – Specular – 8 mm (UNI)				
Surface flame impingement	Fs ≤150 mm	6	50	-
	Ignition of filter paper		-	Compliant
Edge flame Impingement	Fs ≤150 mm	6	30	-
	Ignition of filter paper		-	Compliant

www.trespa.info - IP: 104.23.229.68 - Downloaded on: 2026-10-07 10:55:41
Disclaimer applies. Information indicative and for general informational purposes only. Refer to website terms of use.

Continued test report No. 22082B – Colour difference review

Test method and test number	Parameter	No. tests	Results	
			Continuous parameter – maximum	Compliance with parameters
Kraft + F33 – NW04 – Satin – 8 mm (Printed decors)				
Surface flame impingement	Fs ≤150 mm	6	30	-
	Ignition of filter paper		-	Compliant
Edge flame Impingement	Fs ≤150 mm	6	25	-
	Ignition of filter paper		-	Compliant
Kraft + F33 – C08.03 – Diffuse – 8 mm (Printed decors)				
Surface flame impingement	Fs ≤150 mm	6	40	-
	Ignition of filter paper		-	Compliant
Edge flame Impingement	Fs ≤150 mm	6	30	-
	Ignition of filter paper		-	Compliant

4.3.2 Test report No. 22082C – Single-sided vs Double-sided

Test method and test number	Parameter	No. tests	Results	
			Continuous parameter – maximum	Compliance with parameters
EN ISO 11925-2				
Kraft + F33 – NA17 – Matt Rock – 8 mm (Printed decors - Single-sided)				
Surface flame Impingement	Fs ≤150 mm	6	0	-
	Ignition of filter paper		-	Compliant
Edge flame Impingement	Fs ≤150 mm	6	30	-
	Ignition of filter paper		-	Compliant
Kraft + F33 – NA17 – Matt – 8 mm (Printed decors - Double-sided)				
Surface flame impingement	Fs ≤150 mm	6	0	-
	Ignition of filter paper		-	Compliant
Edge flame Impingement	Fs ≤150 mm	6	30	-
	Ignition of filter paper		-	Compliant

www.trespa.info - IP: 104.23.229.68 - Downloaded on: 2026-10-07 10:55:41
Disclaimer applies. Information indicative and for general informational purposes only. Refer to website terms of use.

4.3.3 Test report No. 22082A – Colour difference review

Test method and test number	Parameter	No. tests	Results	
			Continuous parameter – mean (m)	Compliance with parameters
EN 13823				
Kraft F30 – M51.0.1 Satin – 8 mm Metallics	$FIGRA_{0.2MJ}$ [W/s]	1	65	-
	$FIGRA_{0.4MJ}$ [W/s]		59	-
	THR_{600s} [MJ]		3.3	-
	LFS < edge		-	Compliant
	SMOGRA [m^2/s^2]		6	-
	TSP_{600s} [m^2]		25	-
	Flaming debris - flaming ≤ 10 s - flaming > 10 s		 - -	 Compliant Compliant
Kraft F30 – M53.0.1 Satin – 8 mm Metallics	$FIGRA_{0.2MJ}$ [W/s]	1	70	-
	$FIGRA_{0.4MJ}$ [W/s]		40	-
	THR_{600s} [MJ]		2.7	-
	LFS < edge		-	Compliant
	SMOGRA [m^2/s^2]		6	-
	TSP_{600s} [m^2]		21	-
	Flaming debris - flaming ≤ 10 s - flaming > 10 s		 - -	 Compliant Compliant
Kraft F30 – LM21.8.1 Oblique – 8 mm Metallics	$FIGRA_{0.2MJ}$ [W/s]	1	77	-
	$FIGRA_{0.4MJ}$ [W/s]		59	-
	THR_{600s} [MJ]		3.3	-
	LFS < edge		-	Compliant
	SMOGRA [m^2/s^2]		6	-
	TSP_{600s} [m^2]		21	-
	Flaming debris - flaming ≤ 10 s - flaming > 10 s		 - -	 Compliant Compliant
Kraft F30 – A12.1.8 Satin – 8 mm UNI	$FIGRA_{0.2MJ}$ [W/s]	1	53	-
	$FIGRA_{0.4MJ}$ [W/s]		53	-
	THR_{600s} [MJ]		2.7	-
	LFS < edge		-	Compliant
	SMOGRA [m^2/s^2]		6	-
	TSP_{600s} [m^2]		23	-
	Flaming debris - flaming ≤ 10 s - flaming > 10 s		 - -	 Compliant Compliant

www.trespa.info - IP: 104.23.229.68 - Downloaded on: 2026-10-07 10:55:41
Disclaimer applies. Information indicative and for general informational purposes only. Refer to website terms of use.

Continued test report No. 22082A – Colour difference review

Test method and test number	Parameter	No. tests	Results	
			Continuous parameter – mean (m)	Compliance with parameters
Kraft F30 – A.05.00 Satin – 8 mm UNI	$FIGRA_{0.2MJ}$ [W/s]	1	38	-
	$FIGRA_{0.4MJ}$ [W/s]		38	-
	THR_{600s} [MJ]		2.2	-
	LFS < edge		-	Compliant
	SMOGRA [m^2/s^2]		6	-
	TSP_{600s} [m^2]		21	-
	Flaming debris - flaming ≤ 10 s - flaming > 10 s		- -	Compliant Compliant
Kraft F30 – L90.0.0 Specular – 8 mm UNI	$FIGRA_{0.2MJ}$ [W/s]	1	34	-
	$FIGRA_{0.4MJ}$ [W/s]		34	-
	THR_{600s} [MJ]		2.2	-
	LFS < edge		-	Compliant
	SMOGRA [m^2/s^2]		6	-
	TSP_{600s} [m^2]		16	-
	Flaming debris - flaming ≤ 10 s - flaming > 10 s		- -	Compliant Compliant
Kraft F33 – NW04 Satin – 8 mm Printed decors	$FIGRA_{0.2MJ}$ [W/s]	1	54	-
	$FIGRA_{0.4MJ}$ [W/s]		43	-
	THR_{600s} [MJ]		2.5	-
	LFS < edge		-	Compliant
	SMOGRA [m^2/s^2]		7	-
	TSP_{600s} [m^2]		20	-
	Flaming debris - flaming ≤ 10 s - flaming > 10 s		- -	Compliant Compliant
Kraft F33 – C08.03 Diffuse – 8 mm Printed decors	$FIGRA_{0.2MJ}$ [W/s]	1	71	-
	$FIGRA_{0.4MJ}$ [W/s]		133	-
	THR_{600s} [MJ]		2.8	-
	LFS < edge		-	Compliant
	SMOGRA [m^2/s^2]		7	-
	TSP_{600s} [m^2]		27	-
	Flaming debris - flaming ≤ 10 s - flaming > 10 s		- -	Compliant Compliant

www.trespa.info - IP: 104.23.229.68 - Downloaded on: 2026-10-07 10:55:41
Disclaimer applies. Information indicative and for general informational purposes only. Refer to website terms of use.

Continued test report No. 22082A – Colour difference review

Test method and test number	Parameter	No. tests	Results	
			Continuous parameter – mean (m)	Compliance with parameters
Kraft F33 – NA17 Matt Rock – 8 mm Printed decors	$FIGRA_{0.2MJ}$ [W/s]	1	98	-
	$FIGRA_{0.4MJ}$ [W/s]		56	-
	THR_{600s} [MJ]		3.5	-
	LFS < edge		-	Compliant
	SMOGRA [m^2/s^2]		7	-
	TSP_{600s} [m^2]		29	-
	Flaming debris - flaming ≤ 10 s - flaming > 10 s		- -	Compliant Compliant

4.3.4 Test report No. R0016912 and 22082C – Single-sided vs Double-sided

Test method and test number	Parameter	No. tests	Results	
			Continuous parameter – mean (m)	Compliance with parameters
EN 13823				
Kraft F33 – NA17 Matt Rock – 8 mm Double-sided Printed decors	$FIGRA_{0.2MJ}$ [W/s]	1	89	-
	$FIGRA_{0.4MJ}$ [W/s]		53	-
	THR_{600s} [MJ]		3.4	-
	LFS < edge		-	Compliant
	SMOGRA [m^2/s^2]		7.1	-
	TSP_{600s} [m^2]		26	-
	Flaming debris - flaming ≤ 10 s - flaming > 10 s		- -	Compliant Compliant
Kraft F33 – NA17 Matt Rock – 8 mm Single-sided Printed decors	$FIGRA_{0.2MJ}$ [W/s]	1	75	-
	$FIGRA_{0.4MJ}$ [W/s]		24	-
	THR_{600s} [MJ]		3.4	-
	LFS < edge		-	Compliant
	SMOGRA [m^2/s^2]		6.9	-
	TSP_{600s} [m^2]		25	-
	Flaming debris - flaming ≤ 10 s - flaming > 10 s		- -	Compliant Compliant
Kraft F33 – NA17 Matt – 8 mm Double-sided Printed decors	$FIGRA_{0.2MJ}$ [W/s]		117	-
	$FIGRA_{0.4MJ}$ [W/s]		74	-
	THR_{600s} [MJ]		3.5	-
	LFS < edge		-	Compliant

www.trespa.info - IP: 104.23.229.68 - Downloaded on: 2026-10-07 10:55:41
Disclaimer applies. Information indicative and for general informational purposes only. Refer to website terms of use.

	SMOGRA [m^2/s^2]	1	7	-
	TSP_{600s} [m^2]		23	-
	Flaming debris - flaming ≤ 10 s - flaming > 10 s		- -	Compliant Compliant

4.3.5 Test report No. 22082F – Metallic worse case reproducibility

Test method and test number	Parameter	No. tests	Results	
			Continuous parameter – mean (m)	Compliance with parameters
EN 13823				
Kraft F30 – LM21.8.1 Oblique – 8 mm Double-sided Metallics	$FIGRA_{0.2MJ}$ [W/s]	3	109	-
	$FIGRA_{0.4MJ}$ [W/s]		83	-
	THR_{600s} [MJ]		4.1	-
	LFS < edge		-	Compliant
	SMOGRA [m^2/s^2]		9	-
	TSP_{600s} [m^2]		41	-
	Flaming debris - flaming ≤ 10 s - flaming > 10 s		- -	Compliant Compliant

4.3.6 Test report No. 22082G – UNI worse case reproducibility

Test method and test number	Parameter	No. tests	Results	
			Continuous parameter – mean (m)	Compliance with parameters
EN 13823				
Kraft F30 – A12.1.8 Satin – 8 mm Double-sided UNI	$FIGRA_{0.2MJ}$ [W/s]	3	87	-
	$FIGRA_{0.4MJ}$ [W/s]		57	-
	THR_{600s} [MJ]		3.7	-
	LFS < edge		-	Compliant
	SMOGRA [m^2/s^2]		9	-
	TSP_{600s} [m^2]		35	-
	Flaming debris - flaming ≤ 10 s - flaming > 10 s		- -	Compliant Compliant

www.trespa.info - IP: 104.23.229.68 - Downloaded on: 2026-10-07 10:55:41
Disclaimer applies. Information indicative and for general informational purposes only. Refer to website terms of use.

4.3.7 Test report No. 22082G – Printed worse case reproducibility

Test method and test number	Parameter	No. tests	Results	
			Continuous parameter – mean (m)	Compliance with parameters
EN 13823				
Kraft F30 – NA17 Satin – 8 mm Double-sided Printed decors	$FIGRA_{0.2MJ}$ [W/s]	3	113	-
	$FIGRA_{0.4MJ}$ [W/s]		85	-
	THR_{600s} [MJ]		3.7	-
	LFS < edge		-	Compliant
	SMOGRA [m^2/s^2]		9	-
	TSP_{600s} [m^2]		27	-
	Flaming debris - flaming ≤ 10 s - flaming > 10 s		 - -	 Compliant Compliant

4.4 CLASSIFICATION CRITERIA

Fire classification of construction products and building elements Excluding floorings and linear pipe thermal insulation products			
Classification criteria			
Class Test method(s)	**B**	**C**	**D**
EN ISO 11925-2 Exposure = 30 s	F_s ≤ 150 mm within 60 s Ignition of the paper in EN ISO 11925-2 results in a d2 classification.		
EN 13823	$FIGRA_{0.2\ MJ}$ ≤ 120 W/s LFS < edge of specimen THR_{600s} ≤ 7.5 MJ	$FIGRA_{0.4\ MJ}$ ≤ 250 W/s LFS < edge of specimen THR_{600s} ≤ 15 MJ	$FIGRA_{0.4\ MJ}$ ≤ 750 W/s
Additional classification			
Smoke production	**s1** = SMOGRA ≤ 30 m^2/s^2 and TSP_{600s} ≤ 50 m^2 ; **s2** = SMOGRA ≤ 180 m^2/s^2 and TSP_{600s} ≤ 200 m^2; **s3** = not s1 or s2		
Flaming Droplets/particles	**d0** = no flaming droplets/ particles in EN 13823 within 600 s; **d1** = no flaming droplets/ particles persisting longer than 10 s in EN 13823 within 600 s; **d2** = not d0 or d1.		

www.trespa.info - IP: 104.23.229.68 - Downloaded on: 2026-10-07 10:55:41
Disclaimer applies. Information indicative and for general informational purposes only. Refer to website terms of use.

5. CLASSIFICATION AND FIELD OF APPLICATION

5.1 REFERENCE OF CLASSIFICATION

This classification has been carried out in accordance with clause 11 of EN 13501-1:2018.

5.2 CLASSIFICATION

The product, **Trespa® Meteon® FR**, in relation to its reaction to fire behaviour is classified:

B

The additional classification in relation to smoke production is:

s1

The additional classification in relation to flaming droplets / particles is:

d0

Reaction to fire classification: B – s1, d0

5.3 FIELD OF APPLICATION

5.3.1 Direct field of application

This classification is valid for the following product parameters:

Thickness	≥ 8 mm
Surface density	≥ 11.2 kg/m^2
Other properties	All colours (printed decors, UNI or metallics)

As per NEN-EN 438-7:2005, this classification is valid for the following end use applications:

Substrate	Wood based substrate (Class D-s2, d0 or better) OR Non-combustible (class A1/A2, 870 kg/m³, according to EN 13238:2010) OR No substrate
Insulation	With or without insulation (Class A1/A2 – thickness 50 mm – Density 45 kg/m^3 following requirements of §B.2 of EN 438-7:2005) OR Without insulation
Application	Mounted any types of frames (wood, aluminium, steel)
Air gap	Yes
Methods and means of fixing	Mechanically up to 800 mm
Joints	With open horizontal joints (≤ 10 mm) or any type of closed joints.

www.trespa.info - IP: 104.23.229.68 - Downloaded on: 2026-10-07 10:55:41
Disclaimer applies. Information indicative and for general informational purposes only. Refer to website terms of use.

5.4 DURATION OF THE VALIDITY OF THIS CLASSIFICATION REPORT

Consult classification standard and national laws and regulations for limitations on the period of validity of the classification.

6. LIMITATIONS

This classification document does not represent type approval or certification of the product.

The classification assigned to the product in this report is within the context of system 1 **Assessment and Verification of Consistency of Performance (AVCP)** and **CE marking** under the **Construction Products Regulation**.

The test laboratory has, therefore, played no part in sampling the product for the test, although it holds appropriate references, supplied by the manufacturer, to provide for traceability of the samples tested.

Robin Timmermans

Ondertekend door: Robin TIMMERMANS

Junior Project leader Reaction to Fire

Job Onderwater

Signed by: Job ONDERWATER

Project Leader Reaction to Fire

Suzanne van Herp

Signed by: Suzanne VAN HERP

Project Leader Reaction to Fire

www.trespa.info - IP: 104.23.229.68 - Downloaded on: 2026-10-07 10:55:41
Disclaimer applies. Information indicative and for general informational purposes only. Refer to website terms of use.